

Solid polycarbonate sheet for LED lighting

Your benefits:

- extreme high light reflection and high opacity at the same time
- excellent fire properties
- extreme impact strength
- resistance to wide range of temperature

Solid **Makrolon® RX** sheets are highly reflective opaque solid polycarbonate sheets. **Makrolon® RX** is developed for applications based on LED light sources, which do not emit UV light. It offers a combination of diffuse light reflectance of incident light with the opacity and exhibits excellent fire behavior and high impact strength. Makrolon® sheets resist temperatures of -100 to +120 °C. **Makrolon® RX** sheets can be thermoformed, cut, punched or otherwise fabricated with ease.

Makrolon® RX is an ultra-white opaque sheet offering a combination of high light reflectance in the LED spectral range together with its very high opacity. **Makrolon® RX** exhibits high gloss surface.

Makrolon® RX-FR is a white opaque sheet offering high light reflection in the LED spectral range and exhibits silk-matt surface which aids the diffuse reflectance of the incident light. Highly flame-retarding **Makrolon® RX-FR** comes with a UL listed flammability rating.

Applications:

Typical applications for **Makrolon® RX** sheets are LED light fittings and fixtures, e.g.:

- flat and thermoformed reflectors,
- components of lamp interiors,
- external (housing) parts,
- indirect lighting
- back reflectors in edge-lit panels.

	Test Conditions	Makrolon RX ⁽¹⁾	Makrolon RX-FR ⁽¹⁾	Unit	Test Method
PHYSICAL					
Density		1340	1340	kg/m ³	ISO 1183-1
Water absorption saturation	water at 23°C	0.30	0.30	%	ISO 62
Water absorption equilibrium	23°C, 50 % relative humidity	0.12	0.12	%	ISO 62
MECHANICAL					
Tensile modulus	1 mm/min	2700	2700	MPa	ISO 527-1,-2
Nominal strain at break	50 mm/min	50	50	%	ISO 527-1,-2
Charpy impact strength	23°C, unnotched	non-break	non-break	kJ/m ²	ISO 179-1eU
THERMAL					
Vicat softening temperature	50 N; 50°C/h	140	140	°C	ISO 306
Coefficient of thermal expansion	23 to 55°C	0.65	0.65	10 ⁻⁴ K	ISO 11359-1,-2
ELECTRICAL					
Electrical strength	1 mm	31	34	kV/mm	IEC 60243-1
Volume resistivity		8.2 E14	6 E14	Ohm.m	IEC 60093
Surface resistivity		1 E17	5.3 E16	Ohm	IEC 60093
Relative permittivity	100 Hz	3.5	3.5	-	IEC 60250
Relative permittivity	1 MHz	3.4	3.4	-	IEC 60250
Dissipation factor	100 Hz	8	8	10 ⁻⁴	IEC 60250
Dissipation factor	1 MHz	97	93	10 ⁻⁴	IEC 60250

⁽¹⁾ RX sheet thickness 1/ 2/ 3/ 4 mm (other thickness on request)

⁽¹⁾ RX FR sheet thickness 1,5/ 2/ 3/ 4 mm (other thickness on request)

The manner in which you use and the purpose to which you put and utilize our products, technical assistance and information (whether verbal, written or by way of production evaluations), including any suggested formulations and recommendations, are beyond our control. Therefore, it is imperative that you test our products, technical assistance, information and recommendations to determine to your own satisfaction whether our products, technical assistance and information are suitable for your intended uses and applications. This application-specific analysis must at least include testing to determine suitability from a technical as well as health, safety, and environmental standpoint. Such testing has not necessarily been done by BMS. Unless we otherwise agree in writing, all products are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. It is expressly understood and agreed that you assume and hereby expressly release us from all liability, in tort, contract or otherwise, incurred in connection with the use of our products, technical assistance, and information. Any statement or recommendation not contained herein is unauthorized and shall not bind us. Nothing herein shall be construed as a recommendation to use any product in conflict with any claim of any patent relative to any material or its use. No license is implied or in fact granted under the claims of any patent.

Makrolon® is a registered trademark of Covestro AG

MF 0299 e

Makrolon® RX-Line

Solid polycarbonate sheet for LED lighting

Optical Properties:

Test Method according to EN ISO 13468-2

Dimensions:

Thicknesses: **Makrolon® RX** line will be available in 1.0 - 4.0 mm except for RX-FR: 1.5 - 4.0 mm and RX matte 1.0 mm.

Sizes: **Makrolon® RX** line will be available in 1.250 x 2.050 mm

Makrolon® Type	RX	RX-matte	RX-UV	RX-FR
Light reflectance D65	> 96%	94%	95%	> 94%
YI D65	< 2	< 3	< 3	< 4
gloss60° (ISO 2813)	< 110	< 3	110	< 30

Upon request and quantity requirements, other dimensions can be offered

Permanent Service Temperature:

The permanent service temperature without load is approx. 120 °C.

Fire Rating (*):

Sample thickness (mm)	Makrolon® RX		Makrolon® RX-FR		Makrolon® RX matte
	1.5	3.0	1.5	3.0	1.0
UL 94	V-2**	V-2**	V-0	V-0	V-2**

*) Fire certificates are limited in time and scope, always check if the mentioned certificate is valid for the purchased polycarbonate sheet type at the date of delivery. Polycarbonate sheets may change their fire behavior due to ageing and weathering. The indicated fire rating was tested on new / unweathered Product in accordance with the indicated fire classification standards. **) Only indicative test result, no Yellow Card.

Glow Wire Flammability Tests:

Test method according to IEC 60695-2-12

Glow Wire Flammability Index (GWFI):

Makrolon® RX	1 mm:	850°C
Makrolon® RX,	1.5/3.0 mm:	960°C
Makrolon® RX-FR,	1.5/3.0 mm:	960°C

Glow Wire Ignition Test (GWIT):

Makrolon® RX	1 mm	850°C
Makrolon® RX,	1.5 mm:	825°C
Makrolon® RX,	3.0 mm:	850°C
Makrolon® RX-FR,	1.5/3.0 mm:	850°C



Covestro Deutschland AG
 Kaiser-Wilhelm-Allee 60
 51373 Leverkusen Germania
www.sheeteurope.covestro.com
www.sheets.covestro.com

DISTRIBUTORE

MOHWINCKEL

20090 Trezzano s. Naviglio
 Via S. Cristoforo 78
 Tel. 02 48401749 - Fax 02 4453847
 e-mail: comm@mohwinckel.it